

**EXD200 High Density** Insulation rigid expanded polystyrene boards suitable for a variety of construction applications ranging from below grade insulation and under concrete slabs, to interior/exterior walls, roofs and more.

Meets and/or exceeds **ULC requirements for** foamed plastics Type 2.

### BENEFITS

- Compressive Strength 20 PSI
- Moisture Resistant
- Maintains Long Term Thermal Properties
- Available in custom lengths & thicknesses
- Helps to meet or exceed LEED **Project Criteria**
- Passive House Standards
- 100% Recyclable

### **APPLICATIONS**

- High Density Insulation for Structural Raft Slabs
- Suitable for under concrete slabs, sidewalks, driveways
- Foundation Walls
- Flat/Sloped Roofs
- Television and Film
- Artwork and Signage
- Exterior/Interior Wall Insulation











2455 Milltower Court, Mississauga ON L5N 5Z6 Office: 905.817.1907 Fax: 905.817.9880 www.epsdepotinc.com info@epsdepotinc.com Copyright © 2020 eps DEPOT Inc.



# SPECIFICATIONS Standard Sheets come in 4'x8' and 2'x8' butt edged.

#### Standard Sheets come in 4'x8' and 2'x8' butt edged. Shiplap also available upon request.



### EXD 200 EPS foamed plastic, Type 2 – Material Properties

| EPS Physical Properties  |                           | ASTM<br>Test<br>Method | Property<br>Values |
|--|---------------------------|------------------------|--------------------|
| <b>Thermal Resistance</b> (R-Va<br>(ft <sup>2</sup> •hr•°F/(BTU•in)) | llue per inch)<br>minimum | C518                   | 4.2                |
| Water Vapour Permeanc<br>(ng/Pa•s•m <sup>2</sup> )                   | <b>e</b><br>maximum       | E96                    | 130                |
| Dimensional Stability<br>(% Linear Change)                           | maximum                   | D2126                  | 1.5                |
| Flexural Strength<br>(kPa)   | minimum                   | C203                   | 300                |
| Water Absorption<br>(% by volume)                                    | maximum                   | D2842                  | 2.0                |
| Compressive Strength<br>(kPA / PSI)                                  | minimum                   | D1621                  | 140 / 20           |
| Limiting Oxygen Index (%)  | minimum                   | D2863                  | 24                 |

EXD 200 conforms to CAN/ULC-S701-11 Standard for Thermal Insulation, Polystyrene Board and Pipe Covering Type 2. BOZC7.R27245

## ENVIRONMENTAL IMPACT

EPS has much lower negative environmental impacts than most other foam plastic insulation materials. The Environmental Product Declaration (EPD) has been certified by UL Environment. EPS has no nutritional value for insects. EPS insulation resists mold & fungi growth per ASTM C1338.

# RECYCLING

EPS Depot recycles #6 Expanded Polystyrene (EPS) in a clean, non contaminated, dry form for its' customers. EPS can be recycled for reuse in in various applications including packaging, construction, landscaping, outdoor furniture, and more.

# **PASSIVE HOUSE**

Passive houses are green buildings constructed using a set of international design principles and standards that allow them to use up to 90 per cent less energy for heating and cooling than conventional buildings, thereby producing far fewer greenhouse gas emissions. EXD High Density Insulation is the perfect product to meet and or exceed these requirements, used as the base material for structural raft slabs, or as additional Continuous Insulation on exterior walls. Contact us today for more information.



### **FIRE CHARACTERISTICS**

Expanded Polystyrene is a combustible material and therefore should be protected from open sources of ignition, such as flames and other sources of combustion. Combustible material of an increased thickness or higher density will increase fuel loading and therefore increase measured flame spread ratings when tested in accordance with CAN/ULC S102.2.

# **AVAILABILITY**

EXD200 is manufactured by EPS Depot Inc in Mississauga, ON and available through our distribution network. For your local distributor, contact EPS Depot Inc at 905-817-1907.

# MAINTENANCE

Under normal use, no maintenance is required for EPS. Adequate drainage/ventilation can dry out EPS that became wet, per ASTM C1512 tests.



2455 Milltower Court, Mississauga ON L5N 5Z6 Office: 905.817.1907 Fax: 905.817.9880 **www.epsdepotinc.com** info@epsdepotinc.com



Copyright © 2020 eps DEPOT Inc.